

Technical Data Sheet

Trovidur® PHT

PVC-C

Typical characteristics

- Propiedades físicas uniformes
- Temperatura de servicio continuo hasta 90 °C
- Alta resistencia a ácidos, lejías y soluciones salinas.
- Retardante de llama
- Autoextinguible tras retirar la llama.
- buena soldabilidad
- Buena termoformabilidad
- Good glueability
- Buena resistencia al impacto

Typical industries

- Construcción de contenedores químico
- Tanques de almacenamiento
- Tecnología de salas blancas

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,64
Water absorption	DIN EN ISO 62	%	0,20
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	60
Elongation at break	DIN EN ISO 527	%	15
Tensile modulus of elasticity	DIN EN ISO 527	MPa	3000
Notched impact strength	DIN EN ISO 179	kJ / m ²	6
Shore hardness	DIN EN ISO 868	scale D	82
Thermal properties			
Thermal conductivity	DIN 52612-1	W / (m * K)	0,13
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	107
Service Temperature		°C	-10 ... +90
Coefficient of linear thermal expansion	DIN EN ISO 11359-2	mm/m K	~ 0,075
Glow wire ignition tempearture	DIN EN 60695-2-13	°C	990
Glow wire flammability index	DIN EN 60695-2-12	°C	960

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 26/08/2026 • Release: 20/09/2023 • Version: 1.0
 PIM-ID: 591021 • PIM-Code: 1102-36-27.11.22.16.11.16.34.3.162-9.7.7-5
 Company-IDs: 20000-2

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$>10^{15}$
Surface resistivity	DIN EN 62631-3-2	Ω	$>10^{13}$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 26/08/2026 • Release: 20/09/2023 • Version: 1.0
PIM-ID: 591021 • PIM-Code: 1102-36-27.11.22.16.11.16.34.3.162-9.7.7-5
Company-IDs: 20000-2

Page 2 / 2 (Dates in DD/MM/YYYY)

